Seal 341®

A seal and finish. Formulated to enhance the rich, natural colors of your hard floors without leaving a plastic-looking surface. It also seals resilient tile floors to create a smooth, unbroken base for high speed finishes. Seal 341 is versatile enough to be used as a top coat on resilient floors. Seal 341 not only enhances the natural colors in hard floors, it protects all floors from dirt, spills, and abrasions that come from heavy traffic.

- Formulated to seal porous flooring.
- Easy to apply no matter what the conditions.
- Attractive, low lustre finish.

Technical Specifications

Appearance	Milky Emulsion
Dilution Rate	RTU
Color	White
Scent	Non-Objectionable
Non Volatile Matter	22.00%
pH @ 25 deg. C	8.50 - 9.50

Safety

See material safety data sheet and product for safety information, handling and proper use.

HMIS (Concentrate/RTU)

Flammability = 0 Health = 0 Reactivity = 0

Availability

HIL0034106	4 - 1 Gallon Containers
HIL0034107	1 - 5 Gallon Bag-In-Box
HIL0034109	1 - 55 Gallon Drum

Certifications, Registrations & Notes

UL Approved

Classified by Underwriters Laboratories, Inc. as to slip resistance. (186S).

Directions

Preparation: New floors: For hard floors, allow surfaces to set 30 days to ensure proper curing of Portland terrazzo or grout joints; for resilient flooring, ensure the adhesive has cured for at least 2 weeks. Scrub with a solution of Hillyard Recoat Prep or Assurance, following label directions, and a blue pad. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard Nutra-Rinse and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour. **Scrub and recoat:** Scrub the existing floor polish with a solution of Hillyard Recoat Prep or Assurance, following label directions, and a blue pad. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard Nutra-Rinse and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour. **Stripping:** Strip Seal 341 or other polishes from the floor with a solution of Hillyard Arsenal Stripper, Devastator, or Power-Strip, following label directions. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard Nutra-Rinse and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour.
Synthetic Sports Floors: Always check with the flooring manufacturer's warranty concerning the use of maintenance products on your floor. Once warranty has expired or, at your discretion, you decide to use Seal 341, follow the preparation directions on the Hillyard Salvation label.
Application: When used as a seal, apply a minimum of 2 coats of Seal 341 at a rate of 1500-2000 ft^2/gallon with a microfiber flat finish mop or Multi-Flo XP. Allow each coat to dry a minimum of 30 minutes to 1 hour before applying the next. When used as a seal/finish, apply a minimum of 6 coats of Seal 341.
NOTE: Allow for longer dry time between coats of finish if the humidity is above 80% or the floor temperature is below 60°F (16 °C). For best results, do not apply more than 3-4 coats per day.
Maintenance: Use a cotton dust mop, treated with Hillyard Super Hil-Tone, daily to remove loose dirt and grit. Damp mop or autoscrub, as scheduled, with Hillyard Super Shine-All®, Top Clean®, or Arsenal® Heavy Duty Floor Cleaner. Scrub and recoat, as scheduled, with a minimum of 2 coats of Seal 341.
FLOOR PAD RECOMMENDATIONS: Stripping: black; **Scrub and Recoat:** blue; **Autoscrubbing:** red.
NOTICE: Do not use an ammoniated cleaner for daily care. Do not pour unused seal back into the original container.