New-Jax

ENCORE

Metal Interlocked Acrylic Polymer Floor Finish

See Cautions and First Aid on back panel.
KEEP OUT OF REACH OF CHILDREN.
FOR INSTITUTIONAL AND COMMERCIAL USE.

5 US gal (18.9 L)

RLB4337 0560515

⚠ WARNING
ATENCIÓN

Children can fall into bucket and drown.

Keep children away from buckets with even a small amount of liquid.

Los niños pueden caerse en el balde y ahogarse.

Mantenga los niños alejados de baldes, incluso los que solo contienen una pequeña cantidad de liquido.

RLB4338

New-Jax ENCORE

Metal Interlocked Acrylic Polymer Floor Finish

DIRECTIONS FOR USE: ***Read the entire label before using this product.*** Recommended for use on all types of resilient tile flooring and properly prepared hard surfaces. RESTORATIVE MAINTENANCE: Completely remove all old wax, finish and soil from floor surface following strip procedure instructions on stripper label. Floor surface must be clean, dry and free of residue before finish is applied. Rinse with clean water if necessary. Apply finish in uniform, thin to medium coats using a clean synthetic finish mop, microfiber mop or applicator system. Allow each coat to dry thoroughly before applying additional coats, usually 20 - 30 minutes. Elevated temperatures, heavy coats and humidity may extend dry time. A minimum of 4 coats of finish is recommended. ***Note: This product is a self-sealing finish, however, if tile is old, worn or porous, initially applying 1 - 2 coats of a sealer will enhance gloss and long term performance.*** ROUTINE MAINTENANCE: Sweep large debris and dust mop. Damp mop or automatic scrub using a floor cleaner. Buff or burnish the floor to enhance gloss as needed. Use Cleaner/Restorer to condition the floor and extend the time between top scrub and recoating. INTERIM MAINTENANCE: Sweep large debris and dust mop. Top scrub the floor using maroon pad or equivalent to remove the top soiled layers of finish. Floor surface must be clean, dry and free of residue before finish is applied. Apply 1 - 2 coats of finish as directed above. Please recycle empty containers. ***Note: Slip resistance meets or exceeds standard, (ASTM D 2047-11) James Machine 0.5 minimum.***

Caution: May cause eye irritation. Contains glycol ether. Avoid contact with eyes. Wash thoroughly after handling. Do not ingest.

FIRST AID: If splashed in eyes, flush with large quantities of water. Call a physician if irritation persists. If swallowed, do not induce vomiting. Rinse out mouth with water. Call a physician.

INGREDIENTS (CAS No.): Water (7732-18-5); Acrylate Copolymer (N/A); Diethylene Glycol Ethyl Ether (111-90-0); Tributoxyethyl Phosphate (78-51-3); Wax Emulsion (N/A).

KEEP FROM FREEZING

Sold by: Jackson Newell PAPER COMPANIES

www.newellpaper.com

JACKSON, MS	COLUMBUS, MS	1212 GRAND AVENUE MERIDIAN, MS 39301	HATTIESBURG, MS	DEMOPOLIS, AL
800-844-5449	800-844-1467	800-844-8894	800-530-7537	800-652-2768

Made in USA

0560515