FOR FOOD PLANT AND OTHER INDUSTRIAL USE ONLY.
POUR LA USINE DE NOURRITURE ET TOUT AUTRE USAGE INDUSTRIEL SEULEMENT.

DIRECTIONS FOR USE: Remove any loose rust or scale from the surface with a wire brush. Remove contaminants, such as grease, oil or wax, from the surface with State 999® or SSD® II. Shake can, then spray in even strokes from a distance of 10 - 12 inches until surface is fully coated. Allow 3 - 5 minutes of drying time between coats. Two coats are recommended. Allow 48 hours before applying top coat of paint. Invert can and spray to clear nozzle after each use.

DANGER: Extremely Flammable Aerosol. Contains gas under pressure; may explode if heated. Causes skin irritation. May cause drowsiness or dizziness. May cause damage to organs through prolonged or repeated exposure.

PRECAUTIONS: Keep away from heat, sparks, open flames and hot surfaces. No smoking. Do not spray on an open flame or other ignition source. Pressurized container: Do not pierce or burn, even after use. Wear protective eye protection. Wash hands thoroughly after handling. Avoid breathing fumes, mist, vapors, and spray. Use only outdoors or in a well-ventilated area. **FIRST AID:** IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists: Get medical attention. IF INHALED: Remove person to fresh air and keep comfortable for breathing. Call a poison center or doctor if you feel unwell. **STORAGE:** Store locked up. Protect from sunlight. Do not expose to temperatures exceeding 50°C/122°F. Store in a well-ventilated place. **DISPOSAL:** Dispose of contents and container in accordance with local, state, and national regulations.

SDS available at www.stateindustrial.com or 1-800-782-2436

RUST CONVERTER: MIR: 1.1

MODE D'EMPLOI : Enlever les fragments de rouille ou de tartre avec une brosse métallique, et les dépôts de graisse, cambouis ou cire avec State 999® or SSD® II. Bien agiter et pulvériser régulièrement par pression à environ 25 à 30 cm jusqu'à ce que toute la surface à traiter soit bien recouverte. Laisser sécher pendant 3 à 5 minutes avant de faire une autre application. Deux couches sont recommandées. Laisser sécher pendant 48 heures avant d'appliquer la couche de peinture de finition. Après chaque usage, renverser la bombe et faire quelques pressions pour nettoyer la buse.

DANGER : Aérosol extrêmement inflammable. Contient du gaz sous pression; peut exploser s'il est chauffé. Provoque une irritation de la peau. Peut causer de la somnolence ou des étourdissements. Peut causer des dommages aux organes à la suite d'expositions répétées ou d'une exposition prolongée.

PRÉCAUTIONS : Tenir à l'écart de la chaleur, des étincelles, des flammes nues et des surfaces chaudes. Ne pas fumer. Ne pas pulvériser sur une flamme nue ou une autre source d'inflammation. Contenant sous pression : Ne pas percer ou brûler, même après usage. Portez des gants et des lunettes de protection. Se laver minutieusement les mains après manipulation. Éviter de respirer les vapeurs, brouillard, vapeurs, et spray. Utiliser uniquement à l'extérieur ou dans un endroit bien aéré. **PREMIERS SOINS :** EN CAS DE CONTACT AVEC LES YEUX : Rincer doucement avec de l'eau pendant plusieurs minutes. Retirer les lentilles de contact, si présents et facile à faire. Continuer à rincer. Si l'irritation oculaire persiste : Demandez un avis médical. EN CAS D'INHALATION : Sortir la personne à l'air frais et garder confortable pour respirer. Appeler un centre antipoison ou un médecin si vous ne vous sentez pas bien. **STOCKAGE :** Stocker verrouillé. Protéger de la lumière du soleil. Ne pas exposer à des températures supérieures à 50°C/122°F. Stocker dans un endroit bien ventilé. **DISPOSITION :** Disposer de contenu et contenant conformément aux locaux, d'État, et les réglementations nationales.

La fiche signalétique est disponible à www.stateindustrial.com ou en communiquant au 1-800-782-2436.

CONVERTISSEUR DE ROUILLE : MIR : 1.1

INGREDIENTS/INGRÉDIENTS: Acetone (67-64-1), Butane (106-97-8), Isopropanol (67-63-0), Propane (74-98-6), 2-Butoxyethanol (111-76-2).

Seller shall not be liable for consequential, special, or indirect damages from use or handling of their product and liability is expressly limited to the refund of purchase price or replacement of product.

State Industrial Products
5915 Landerbrook Drive
Mayfield Heights, OH 44124
To Order Call: 1-866-747-2229
www.stateindustrial.com

6935 Davand Drive
Mississauga, Ontario L5T 1L5
To Order Call: 1-800-668-6513

Royal Industrial Park, Bldg "M"
Local #5, Carr 869, km 1.5 Palmas
Cataño, P.R. 00962
To Order Call: 787-275-3185

SDS AND PRODUCT INFORMATION

MADE IN THE USA

HMIS: 2 - HEALTH; 4 - FLAMMABILITY; 1 - REACTIVITY; B - PROTECTIVE EQUIPMENT
12R12
© Copyright 2021 - State Industrial Products Corp.

600002153

Product #121925

RUST CONVERSION AEROSOL
CONVERTISSEUR DE ROUILLE AÉROSOL

www.stateindustrial.com

State® Since 1911

CONVERTER COAT

Rust Conversion Aerosol
Convertisseur de rouille Aérosol

- Effectively deactivates rust, converting rust into a protective black coating
- Prepares rusted surfaces for a top coat of paint
- Temperature resistant: Withstands hot and cold conditions

NET WT. / POIDS NET:
13 OZ. (369 g)

Care For Work Environments®