


Buckeye®

# Citation®

SEALER / FINISH



## Available Packaging



## The Citation Difference

**Citation** maintains its beautiful high gloss with minimal maintenance time. Regardless of the maintenance program, equipment, or timetable you're working with, **Citation** keeps its radiant gloss.



## FEATURES

### Easy to Apply

- **Self-Leveling** — Coats apply easily
- **Dries rapidly** — Reduces labor costs
- **Builds to a radiant gloss**

### Highly Durable

- **Non-Powdering** — Finish stays intact to last longer
- **Non-Yellowing** — Extends stripping intervals, reducing labor cost
- **Holds up under extreme conditions**

### Easy to Maintain

- **Does not require buffing**
- **Detergent resistant** — Holds up to repeated moppings
- **Resists scuffs** — Floors look better longer

### Versatile

- **Resilient floors** — Vinyl, rubber, asphalt, vinyl composition tile
- **Hard floors** — Terrazzo, slate, marble, concrete, quarry tile
- **Can be buffed at any speed**

## DIRECTIONS FOR USE

### FLOOR PREPARATION:

1. Strip floor thoroughly, using a recommended Buckeye floor stripper according to directions.
2. Pick up spent solution with mop or wet vacuum as soon as each floor section has been stripped. Do not allow solution to dry.
3. Rinse floor thoroughly with clear water. Change rinse water frequently to prevent redepositing of dirt and stripper residue.
4. Allow floor to dry thoroughly before applying Buckeye **Citation**.

### APPLICATION:

1. Use a clean bucket and a clean rayon mop reserved only for floor finish application.
2. Saturate mop thoroughly, press firmly into wringer to remove excess finish. Do not wring.
3. Apply **Citation**. Excellent results are obtained by applying even coats.
4. Allow each coat to dry thoroughly, usually 20 to 30 minutes under normal humidity conditions.

### MAINTENANCE:

1. Dust mop floor with a Buckeye **Aqua Dust™** treated dust mop.
2. Damp mop as required, using Buckeye **Blue** or **Straight-Up®** at 1:64 (2 oz/1 gal. water).
3. If desired, spray buff **Citation** with Buckeye **Equity™** or Buckeye **R.P.M.™** (see data sheets for specific instructions) or dry buff.

### TECHNICAL SPECIFICATIONS

pH	8.4 ± 0.2
Leveling	Excellent
Freeze/Thaw Stability	Pass 3 cycles
Removability	Excellent
Drying Time	20–30 minutes
Black Mark Resistance	Excellent
Film Color	Water Clear
Scrubability	Excellent
Weight/Gallon	8.6 lbs
Slip Resistance	UL Classified



FLOOR  
COATING AND  
FINISHING  
MATERIAL AS  
TO SLIP  
RESISTANCE  
ONLY. 169S

**BUCKEYE INTERNATIONAL, INC.**

2700 WAGNER PLACE • MARYLAND HEIGHTS • MO 63043 • USA • 800.321.2583

[www.buckeyeinternational.com](http://www.buckeyeinternational.com)