

Diversey

# TimeSaver SR™/MC

## Ultra High Solids Finish



An ultra-high solids scrub and recoat finish that does exactly what it says – saves time and money.

### Labor Savings

- Requires fewer initial coats and typically only one coat when recoating to achieve a high gloss appearance level

### Easy-to-Use

- No special applicator or equipment required
- Grab your mop and bucket and you're ready to go

### Superior Gloss

- Provides excellent initial gloss and gloss retention, even with fewer coats

### Excellent Durability

- Exceptional resistance to scratching, scuffing and black heel marks

### Low Odor

- Ideal for use in patient rooms, busy hallways, aisles and 24-hour facilities

# TimeSaver SR™/MC

## Ultra High Solids Finish



### Use Directions

- Blockade areas to be stripped or finished. Floors will be very slippery until dry.
- Strip floor using a Diversey stripper per the instructions on the stripper label.

### Coating

- Using a clean mop, apply a maximum of 3 medium coats of TimeSaver SR™/MC Ultra High Solids Finish. After 24 hours, additional coats may be applied until desired gloss is achieved.
- Allow 30–40 minutes drying time between coats. Temperature, humidity and ventilation may affect drying time. Allow finish to cure for 24 hours before burnishing or applying extra coats. Apply no more than 3 coats in a 24-hour period.

### Maintenance

- Dust mop or sweep.
- Clean the floor with a mop or an automatic scrubber using the recommended Diversey brand cleaner according to label directions.

- To enhance appearance, use any of the following methods: Spray Buff with Diversey brand spray buff, a red pad and 175–1500 rpm equipment. Dry buff using a medium to aggressive pad and 1000–1500 rpm equipment. Ultra-high speed burnish using a medium to aggressive pad and 2000 rpm equipment.

### Recoating

- Dust mop or sweep.
- Clean the floor with a mop or an automatic scrubber using the recommended Diversey brand cleaner according to label directions.
- Blockade area and apply 1–2 uniform coats of finish using a clean mop. Allow finish to cure for 24 hours before burnishing.

### Product Specifications

Description	
Color/Form	White liquid
Flash Point	>200° F (>93.3° C)
pH	8.1
Scent	Ammonia
Shelf Life	2 years
Slip Resistance	0.5 minimum (ASTM D2047)
Solids %	31
Solubility	Dispersible
Specific Gravity	1.08

### Available Items

Product Code	Description/Package Size	Dilution
3137723	4 x 1 gallon / 3.78 L Containers	Ready-to-Use
5104984	1 x 5 gallon / 18.9 L Envirobox™/MC (TrailBlazer™/MC ready)	Ready-to-Use

### Safety Reminder

Please make sure your employees read and understand the product label and Safety Data Sheet before using this product. The label contains directions for use, and both the label and SDS contain hazard warnings, precautionary statements and first aid procedures. SDSs are available on-line at [www.sealedair.com](http://www.sealedair.com) or by calling 888 352 2249. Improper use or dilution may result in damage to surfaces and may result in health and physical hazards that match those of the concentrate. Please refer to the Diversey HazMat Library, only available through Internet Explorer, <http://naextranet.diversey.com/dot/>, for up to date shipping information.